



OHORONGO
cement



PORTLAND LIMESTONE CEMENT

CEM II A-LL 42.5N

COMPOSITION

Ohorongo CEM II A-LL 42.5N Portland Limestone Cement is a hydraulic binder according to SANS 50197/NAMS 197.

The main component is Portland cement clinker, finely ground together with high quality limestone and calcium sulphate, which controls the setting time of Ohorongo CEM II A-LL 42.5N.

Stringent production control during the entire production process ensures consistent high quality.

SPECIFICATION

Ohorongo CEM II A-LL 42.5N Portland Limestone Cement is designed to meet a strength class 42.5 with a normal early strength "N".

The "LL" indicates limestone of high quality and "A" represents 6%-20% of mass.

APPLICATION

Ohorongo CEM II A-LL 42.5N Portland Limestone Cement can be used in applications where a higher strength class is required.

Typical applications are ready-mix concrete, structural concrete, precast products, small scale brick and block making and shotcrete.

- Higher range of concrete strengths can be achieved
- Higher strength class of concrete

Ohorongo CEM II A-LL 42.5N is compatible with commercial chemical admixtures.

STORAGE

Ohorongo Cement is distributed in 50 kg bags, 2 ton bags and bulk tankers. Bulk storage silos should be dry and vapor tight. Cement bags should be protected from moisture and kept dry, preferably off ground by means of pallets or timber, preventing moisture contact. Bags should be stored away from direct sunlight, or should be covered by a roof or sheeting. Stacking should be kept to a maximum of two pallets high to avoid compaction of cement bags at the bottom.

HANDLING AND SAFETY

Refer to **Ohorongo Cement** Safety Data Sheet, obtainable from **Ohorongo Cement**.

TECHNICAL SUPPORT

Ohorongo Cement offers technical support from its comprehensively equipped chemical-, cement-, and concrete laboratories. Assistance to cement- as well as concrete aspects, including advice on mix design is available from our qualified technical staff.

PRICE

Please contact the **Ohorongo Cement** Sales Office for price enquiries. Contact details provided below.

CONTACT

Ohorongo House

Schanzenweg 35 , Windhoek
PO Box 86842, Eros Windhoek
Tel: +264 61 389 300
Fax: +264 61 247 878

Cement Plant

Sargberg Plant, North Otavi
PO Box 444, Tsumeb
Tel: +264 67 235 7000
Fax: +264 67 235 7070

Website:

www.Ohorongo-cement.com



The information given in this publication is based on current knowledge and experience. It gives a general indication of basic suitability, but must be adapted by the user for the particular application by means of tests and trials.

The respective applicable laws, standards and directives and the general recognized civil engineering regulations must be observed. The right to make changes in the interests of product and application development is reserved. Our current Terms and Conditions of Sale and Delivery shall apply for all business transactions.



NAMIBIA 1977

PRODUCED IN NAMIBIA TO
WORLD -CLASS STANDARDS



OHORONGO
cement